

OVERTURE SILK PLA TECHNICAL DATA SHEET

OVERTURE SILK PLA is a PLA with silk finishing designed, providing ease of use, printing quality, speed and reliability.

Physical Properties

Property	Testing method	Typical value
Density	ISO 1183, GB/T 1033	1.19 (g/cm ³ at 21.5 °C)
Vicat Softening temperature*	ISO 306 GB/T 1633	N/A
Melt index	190 °C, 2.16 kg	12.8 (g/10 min)
Melting temperature	DSC, 10 °C/min	153 (°C)

Tested with 3D printed specimen of 100% infill

Mechanical Properties

Property	Testing method	Typical value
Young's modulus (X-Y)	ISO 527, GB/T 1040	3173 ± 97 (MPa)
Tensile strength (X-Y)	ISO 527, GB/T 1040	55.2 ± 2.1 (MPa)
Tensile strength (Z)	ISO 527, GB/T 1040	18.9 ± 3.4 (MPa)
Elongation at break (X-Y)	ISO 527, GB/T 1040	3.5 ± 0.6 (%)
Bending modulus (X-Y)	ISO 178, GB/T 9341	3518 ± 49 (MPa)
Bending strength (X-Y)	ISO 178, GB/T 9341	87.1 ± 1.4 (MPa)
Notched Charpy impact strength (X-Y)	ISO 179, GB/T 1043	2.87 ± 0.08 (kJ/m ²)

All testing specimens were printed under the following conditions: nozzle temperature = 205 °C, printing speed = 60 mm/s, build plate temperature = 40 °C, infill = 100% All specimens were conditioned at room temperature for 24h prior to testing

Recommended printing conditions

Nozzle temperature	190 - 230 (°C)
Build Surface material	OVERTURE Build Surface, Textured PEI
Build surface treatment	None, Applying PVA glue to the build surface
Build plate temperature	25 - 60 (°C)
Cooling fan	Turned on
Printing speed	40-60 (mm/s)
Raft separation distance	0.1-0.2 (mm)
Retraction distance	1-3(mm)
Retraction speed	20-40 (mm/s)
Threshold overhang angle	60 (°)

Based on 0.4 mm nozzle. Printing conditions may vary with different nozzle diameters

Disclaimer:

The typical values presented in this data sheet are intended for reference and comparison purposes only. They should not be used for design specifications or quality control purposes. Actual values may vary significantly with printing conditions. End- use performance of printed parts depends not only on materials, but also on part design, environmental conditions, printing conditions, etc. Product specifications are subject to change without notice.

Each user is responsible for determining the safety, lawfulness, technical suitability, and disposal/recycling practices of OVERTURE materials for the intended application. OVERTURE makes no warranty of any kind, unless announced separately, to the fitness for any use or application. OVERTURE shall not be made liable for any damage, injury or loss induced from the use of OVERTURE materials in any



July. 2024

Version 5.1

application.